




## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification n <sup>o</sup> 6 : <b>H01L 33/00</b>		<b>A1</b>	(11) International Publication Number: <b>WO 99/26299</b>
			(43) International Publication Date: 27 May 1999 (27.05.99)
(21) International Application Number: <b>PCT/US98/23984</b>		(81) Designated States: CA, JP, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).	
(22) International Filing Date: 10 November 1998 (10.11.98)			
(30) Priority Data: 08/969,302 13 November 1997 (13.11.97) US		<b>Published</b> <i>With international search report. Before the expiration of the time limits for amending the claims and to be republished in the event of the receipt of amendments.</i>	
(71) Applicant: MASSACHUSETTS INSTITUTE OF TECHNOLOGY [US/US]; 77 Massachusetts Avenue, Cambridge, MA 02139 (US).			
(72) Inventors: BAWENDI, Mounji; Apartment 2B, 285 Beacon Street, Boston, MA 02116 (US). JENSEN, Klavs, F.; 103 Outlook Drive, Lexington, MA 02173 (US). DABBOUSI, Bashire, O.; Saudi Aramco, P.O. Box 10125, Dharan, 31311 (SA). RODRIGUEZ-VIELO, Javier; Cami de Can Gatzet, 57 3-1, E-08190 San Cugat del Valles (ES). MIKULEC, Frederic, Victor; Apartment 2, 96 Willow Avenue, Somerville, MA 02144 (US).			
(74) Agent: SCOZZAFAVA, Mary, Rose; Choate, Hall & Stewart, Exchange Place, 53 State Street, Boston, MA 02109 (US).			

(54) Title: HIGHLY LUMINESCENT COLOR-SELECTIVE MATERIALS



## (57) Abstract

A coated nanocrystal capable of light emission includes a substantially monodisperse nanoparticle selected from the group consisting of CdX, where x = S, Se, Te and an overcoating of ZnY, where Y = S, Se, uniformly deposited thereon, said coated nanoparticle characterized in that when irradiated the particles exhibit photoluminescence in a narrow spectral range of no greater than about 60 nm, and most preferably 40 nm, at full width half max (FWHM). The particle size of the nanocrystallite core is in the range of about 2 nm (20 Å) to about 12.5 nm (125 Å), with a deviation of less than 10 % in the core. The coated nanocrystal exhibits photoluminescence having quantum yields of greater than 30 %.

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

## HIGHLY LUMINESCENT COLOR-SELECTIVE MATERIALS

## Field of the Invention

5            This invention relates to luminescent nanocrystalline materials which emit visible light over a very narrow range of wavelengths. The invention further relates to materials which emit visible light over a narrow range tunable over the entire visible spectrum.

10 **Background of the Invention**

Semiconductor nanocrystallites (quantum dots) whose radii are smaller than the bulk exciton Bohr radius constitute a class of materials intermediate between molecular and bulk forms of matter. Quantum confinement of both the electron and hole in all three dimensions leads to an increase in the effective band gap of the material with decreasing crystallite size. Consequently, both the optical absorption and emission of quantum dots shift to the blue (higher energies) as the size of the dots gets smaller.

Bawendi and co-workers have described a method of preparing monodisperse semiconductor nanocrystallites by pyrolysis of organometallic reagents injected into a hot coordinating solvent (*J. Am. Chem. Soc.*, **115**:8706 (1993)). This permits temporally discrete nucleation and results in the controlled growth of macroscopic quantities of nanocrystallites. Size selective precipitation of the crystallites from the growth solution provides crystallites with narrow size distributions. The narrow size distribution of the quantum dots allows the possibility of light emission in very narrow spectral widths.

Although semiconductor nanocrystallites prepared as described by Bawendi and co-workers exhibit near monodispersity, and hence, high color selectivity, the luminescence properties of the crystallites are poor. Such crystallites exhibit low photoluminescent yield, that is, the light emitted upon irradiation is of low intensity. This is due to energy levels at the surface of the crystallite which lie within the energetically forbidden gap of the bulk interior. These surface energy states act as traps for electrons and holes which degrade the luminescence properties of the material.

In an effort to improve photoluminescent yield of the quantum dots, the nanocrystallite surface has been passivated by reaction of the surface atoms of the quantum dots with organic passivating ligands, so as to eliminate forbidden energy levels. Such passivation produces an atomically abrupt increase in the chemical potential at the interface of the semiconductor and passivating layer (See, A.P. Alivisatos, *J. Phys. Chem.* **100**:13226 (1996)). Bawendi et al. (*J. Am. Chem. Soc.*, **115**:8706 (1993)) describe CdSe nanocrystallites capped with organic moieties such as tri-*n*-octyl phosphine (TOP) and tri-*n*-octyl phosphine oxide (TOPO) with quantum yields of around 5-10%.

Passivation of quantum dots using inorganic materials also has been reported. Particles passivated with an inorganic coating are more robust than organically passivated dots and have greater tolerance to processing conditions necessary for their incorporation into devices. Previously reported inorganically passivated quantum dot structures include CdS-capped CdSe and CdSe-capped CdS (Tian et al., *J. Phys. Chem.* **100**:8927 (1996)); ZnS grown on CdS (Youn et al., *J. Phys. Chem.* **92**:6320 (1988)); ZnS on CdSe and the inverse structure (Kortan et al., *J. Am. Chem. Soc.* **112**:1327 (1990)); and SiO<sub>2</sub> on Si (Wilson et al., *Science* **262**:1242 (1993)). These reported quantum dots exhibit very low quantum efficiency and hence are not commercially useful in light emitting applications.

M.A. Hines and P. Guyot-Sionnest report the preparation of ZnS-capped CdSe nanocrystallites which exhibited a significant improvement in luminescence yields of up to 50% quantum yield at room temperature (*J. Phys. Chem.* **100**:468 (1996)). However, the quality of the emitted light remained unacceptable because of the large size distribution (12-15% rms) of the core of the resulting capped nanocrystallites. The large size distribution resulted in light emission over a wide spectral range. In addition, the reported preparation method does not allow control of the particle size obtained from the process and hence does not allow control of color.

Danek *et al.* report the electronic and chemical passivation of CdSe nanocrystals with a ZnSe overlayer (*Chem. Materials* **8**:173 (1996)). Although it might be expected that such ZnSe-capped CdSe nanocrystallites would exhibit as good as or better quantum yield than the ZnS analogue due to the better unit cell

matching of ZnSe, in fact, the resulting material showed only disappointing improvements in quantum efficiency ( $\leq 0.4\%$  quantum yield).

Thus there remains a need for semiconductor nanocrystallites capable of light emission with high quantum efficiencies throughout the visible spectrum, which possess a narrow particle size (and hence with narrow photoluminescence spectral range).

It is the object of the invention to provide semiconductor nanocrystallites which overcome the limitations of the prior art and which exhibit high quantum yields with photoluminescence emissions of high spectral purity.

### Summary of the Invention

In one aspect of the invention, a coated nanocrystal capable of light emission includes a substantially monodisperse core selected from the group consisting of CdX, where X = S, Se, Te; and an overcoating of ZnY, where Y = S, Se, and mixtures thereof uniformly deposited thereon, said coated core characterized in that when irradiated the particles emit light in a narrow spectral range of no greater than about 40 nm at full width half max (FWHM). In some embodiments, the narrow spectral range is selected from the spectrum in the range of about 470 nm to about 620 nm and the particle size of the core is selected from the range of about 20 Å to about 125 Å.

In other embodiments of the invention, the coated nanocrystal is characterized in that the nanocrystal exhibits less than a 10% and preferably less than 5%, rms deviation in diameter of the core. The nanocrystal preferably exhibits photoluminescence having quantum yields of greater than 30%, and most preferably in the range of about 30 to 50%.

In another embodiment of the invention, the overcoating comprises one to two monolayers of ZnY. The nanocrystal may further comprise an organic layer on the nanocrystal outer surface. The organic layer may be comprised of moieties selected to provide compatibility with a suspension medium, such as a short-chain polymer terminating in a moiety having affinity for a suspending medium, and moieties which demonstrate an affinity to the quantum dot surface. The affinity for

the nanocrystal surface promotes coordination of the organic compound to the quantum dot outer surface and the moiety with affinity for the suspension medium stabilizes the quantum dot suspension.

5 In another aspect of the invention, a method of preparing a coated nanocrystal capable of light emission includes introducing a substantially monodisperse first semiconductor nanocrystal and a precursor capable of thermal conversion into a second semiconductor material into a coordinating solvent. The coordinating solvent is maintained at a temperature sufficient to convert the precursor into the second semiconductor material yet insufficient to substantially alter the monodispersity of the  
10 first semiconducting nanocrystal and the second semiconductor material has a band gap greater than the first semiconducting nanocrystal. An overcoating of the second semiconductor material is formed on the first semiconducting nanocrystal.

In one embodiment of the invention, the monodispersity of the nanocrystal is monitored during conversion of the precursor and overcoating of the first  
15 semiconductor nanocrystal. In another embodiment, an organic overcoating is present on the outer nanocrystal surface, obtained by exposing the nanocrystal to an organic compound having affinity for the nanocrystal surface, whereby the organic compound displaces the coordinating solvent.

In addition to having higher quantum efficiencies, ZnS overcoated particles  
20 are more robust than organically passivated nanocrystallites and are potentially more useful for optoelectronic devices. The (CdSe)ZnS dots of the invention may be incorporated into electroluminescent devices (LEDs). In addition, the (CdSe)ZnS dots of the invention may exhibit cathodoluminescence upon excitation with both high and low voltage electrons and may be potentially useful in the production of  
25 alternating current thin film electroluminescent devices (ACTFELD). In the naming convention used herein to refer to capped nanocrystallites, the compound found within parentheses represents the core compound (i.e. the bare "dot"), while the compound which follows represents the overcoated passivation layer.

These and other features and advantages of the invention are set forth in the  
30 description of the invention, which follows.

### Brief Description of the Drawing

The invention is described with reference to the figures, which are presented for the purpose of illustration only, and in which:

Figure 1 shows the absorption spectra of CdSe dots with diameters measuring  
5 (a) 23 Å, (b) 42 Å, (c) 48 Å and (d) 55 Å before (dashed lines) and after (solid lines)  
overcoating with 1-2 monolayers of ZnS

Figure 2 shows the room temperature photoluminescence (PL) spectra of the  
samples of Figure 1 before (dashed lines) and after (solid lines) overcoating with ZnS;

Figure 3 is a color photograph which illustrates the wide spectral range of  
10 luminescence from and color purity of the (CdSe)ZnS composite quantum dots of the  
present invention;

Figure 4 shows the progression of the absorption spectra for (CdSe)ZnS  
quantum dots with ZnS coverages of approximately 0, 0.65, 1.3, 2.6 and 5.3  
monolayers; and

15 Figure 5 shows the evolution of the PL for ~40 Å diameter (CdSe)ZnS dots of  
Figure 4 with varying ZnS coverage,

### Detailed Description of the Invention

The present invention is directed to the preparation of a series of room  
20 temperature, highly luminescent ZnS-capped CdSe ((CdSe)ZnS) nanocrystallites  
having a narrow particle size distribution. Nanocrystallites of the present invention  
exhibit high quantum yields greater than about 30% and preferably in the range of  
about 30-50% and a narrow band edge luminescence spanning most of the visible  
spectrum from 470 nm to 625 nm. The core of the nanocrystallites is substantially  
25 monodisperse. By monodisperse, as that term is used herein, it is meant a colloidal  
system in which the suspended particles have substantially identical size and shape.  
For the purposes of the present invention, monodisperse particles deviate less than  
10% in rms diameter in the core, and preferably less than 5% in the core.

When capped quantum dots of the invention are illuminated with a primary  
30 light source, a secondary emission of light occurs of a frequency that corresponds to  
the band gap of the semiconductor material used in the quantum dot. As previously  
discussed, the band gap is a function of the size of the nanocrystallite. As a result of

the narrow size distribution of the capped nanocrystallites of the invention, the illuminated quantum dots emit light of a narrow spectral range resulting in high purity light. Spectral emissions in a narrow range of no greater than about 60 nm, preferably 40 nm and most preferably 30 nm at full width half max (FWHM) are observed.

5           The present invention also is directed to a method of making capped quantum dots with a narrow particle size distribution. The capped quantum dots of the invention may be produced using a two step synthesis in which a size selected nanocrystallite is first synthesized and then overcoated with a passivation layer of a preselected thickness. In preferred embodiments, processing parameters such as  
10   reaction temperature, extent of monodispersity and layer thickness may be monitored during crystal growth and overcoating to provide a coated quantum dot of narrow particle size distribution, high spectral purity and high quantum efficiency. "Quantum yield" as that term is used herein, means the ratio of photons emitted to that absorbed, e.g., the photoluminescence quantum yield.

15           The method is described for a (CdSe)ZnS quantum dot, but it is understood that the method may be applied in the preparation of a variety of known semiconductor materials. The first step of a two step procedure for the synthesis of (CdSe)ZnS quantum dots involves the preparation of nearly monodisperse CdSe nanocrystallites. The particles range in size from about 23Å to about 55Å with a  
20   particle size distribution of about 5-10 % . These dots are referred to as "bare" dots. The CdSe dots are obtained using a high temperature colloidal growth process, followed by size selective precipitation.

          The high temperature colloidal growth process is accomplished by rapid injection of the appropriate organometallic precursor into a hot coordinating solvent  
25   to produce a temporally discrete homogeneous nucleation. Temporally discrete nucleation is attained by a rapid increase in the reagent concentration upon injection, resulting in an abrupt supersaturation which is relieved by the formation of nuclei and followed by growth on the initially formed nuclei. Slow growth and annealing in the coordinating solvent results in uniform surface derivatization and regularity in the  
30   core structure.

          Injection of reagents into the hot reaction solvent results in a short burst of homogeneous nucleation. The depletion of reagents through nucleation and the



sudden temperature drop associated with the introduction of room temperature reagents prevents further nucleation. The solution then may be gently heated to reestablish the solution temperature. Gentle reheating allows for growth and annealing of the crystallites. The higher surface free energy of the small crystallites makes them less stable with respect to dissolution in the solvent than larger crystallites. The net result of this stability gradient is the slow diffusion of material from small particles to the surface of large particles ("Ostwald ripening"). Growth of this kind results in a highly monodisperse colloidal suspension from systems which may initially be highly polydisperse.

Both the average size and the size distribution of the crystallites in a sample are dependent on the growth temperature. The growth temperature necessary to maintain steady growth increases with increasing average crystal size. As the size distribution sharpens, the temperature may be raised to maintain steady growth. As the size distribution sharpens, the temperature may be raised in 5-10 °C increments to maintain steady growth. Conversely, if the size distribution begins to spread, the temperature may be decreased 5-10 °C to encourage Ostwald ripening and uniform crystal growth. Generally, nanocrystallites 40 Angstroms in diameter can be grown in 2-4 hours in a temperature range of 250-280 °C. Larger samples (60 Angstroms or more) can take days to grow and require temperatures as high as 320 °C. The growth period may be shortened significantly (e.g., to hours) by using a higher temperature or by adding additional precursor materials.

Size distribution during the growth stage of the reaction may be approximated by monitoring the absorption line widths of the particles. Modification of the reaction temperature in response to changes in the absorption spectrum of the particles allows the maintenance of a sharp particle size distribution during growth. It is also contemplated that reactants could be added to the nucleation solution during crystal growth to grow larger crystals.

The particle size distribution may be further refined by size selective precipitation. In a preferred embodiment, this may be accomplished by manipulation of solvent composition of the nanocrystallite suspension.

The CdSe nanocrystallites are stabilized in solution by the formation of a lyophilic coating of alkyl groups on the crystallite outer surface. The alkyl groups are provided by the coordinating solvent used during the growth period. The interparticle repulsive force introduced by the lyophilic coating prevents aggregation of the particles in solution. The effectiveness of the stabilization is strongly dependent upon the interaction of the alkyl groups with the solvent. Gradual addition of a non-solvent will lead to the size-dependent flocculation of the nanocrystallites. Non-solvents are those solvents in which the groups which may be associated with the crystallite outer surface show no great affinity. In the present example, where the coordinating group is an alkyl group, suitable non-solvents include low molecular weight alcohols such as methanol, propanol and butanol. This phenomenon may be used to further narrow the particle size distribution of the nanocrystallites by a size-selective precipitation process. Upon sequential addition of a non-solvent, the largest particles are the first to flocculate. The removal of a subset of flocculated particles from the initial solution results in the narrowing of the particle size distribution in both the precipitate and the supernatant.

A wealth of potential organometallic precursors and high boiling point coordinating solvents exist which may be used in the preparation of CdSe dots. Organometallic precursors are selected for their stability, ease of preparation and clean decomposition products and low cracking temperatures. A particularly suitable organometallic precursor for use as a Cd source include alkyl cadmium compounds, such as  $\text{CdMe}_2$ . Suitable organometallic precursors for use as a Se source include, bis(trimethylsilyl)selenium  $(\text{TMS})_2\text{Se}$ , (tri-*n*-octylphosphine)selenide (TOPSe) and trialkyl phosphine selenides, such as (tri-*n*-butylphosphine)selenide (TBPSe). Other suitable precursors may include both cadmium and selenium in the same molecule. Alkyl phosphines and alkyl phosphine oxides may be used as a high boiling coordinating solvent; however, other coordinating solvents, such as pyridines, furans, and amines may also be suitable for the nanocrystallite production.

The preparation of monodisperse CdSe quantum dots has been described in detail in Murray *et al.* (*J. Am. Chem. Soc.*, 115:8706 (1993)), which is hereby incorporated in its entirety by reference.

Next, the CdSe particles are overcoated by introducing a solution containing zinc and sulfur precursors in a coordinating solvent (e.g., TOP) into a suspension of CdSe nanocrystallites at the desired temperature. The temperature at which the dots are overcoated is related to the quality of the resultant composite particle.

- 5 Overcoating the CdSe particles at relatively higher temperatures may cause the CdSe seed crystals to begin to grow via Ostwald ripening and deterioration of the size distribution of the particles leading to broader spectral line widths. Overcoating the particles at relatively low temperatures could lead to incomplete decomposition of the precursors or to reduced crystallinity of the ZnS shell. An ideal growth temperature
- 10 may be determined for each CdSe core size to ensure that the size distribution of the cores remains constant and that shells with a high degree of crystallinity are formed. In preferred embodiments, CdSe crystallites are overcoated using diethyl zinc and hexamethyldisilathiane as the zinc and sulfur precursors. CdSe crystallites having a diameter in the range of about 23Å-30Å are overcoated at a temperature in the range
- 15 of about 135-145 °C, and preferably about 140 °C. Similarly, nanocrystallites having a diameter of about 35Å, 40Å, 48Å, and 55Å, respectively, are overcoated at a temperature of about 155-165 °C, and preferably about 160 °C, 175-185 °C and preferably about 180 °C, about 195-205 °C, and preferably about 200 °C, and about
- 20 215-225 °C, and preferably about 220 °C, respectively. The actual temperature ranges may vary, dependent upon the relative stability of the precursors and the crystallite core and overlayer composition. These temperature ranges may need to be modified 10-20 °C, depending upon the relative stability of the precursors. For example, when the more stable trialkyl phosphine chalcogenides (like TOPSe) are used, higher temperatures are employed. The resulting (CdSe)ZnS composite
- 25 particles are also passivated with TOPO/TOP on their outermost surface.

- The ZnS precursor solution concentration and the rate of its addition to the CdSe particles is selected to promote heterogeneous growth of ZnS onto the CdSe nuclei instead of homogeneous nucleation to produce ZnS particles. Conditions favoring heterogeneous growth include dropwise addition, e.g., 1-2 drops/second, of
- 30 the ZnS precursor solution to the CdSe solution and maintenance of the ZnS precursor solution at low concentrations. Low concentrations typically range from 0.0005-0.5 M. In some preferred embodiments, it may be desirable to include a final purification

step in which the overcoated dots are subjected to size selective precipitation to further assure that mainly only (CdSe)ZnS composite particles are present in the final product.

5 In other embodiments, it may be desirable to modify the crystallite outer surface to permit formation of stable suspensions of the capped quantum dots. The outer surface of the nanocrystal includes an organic layer derived from the coordinating solvent used during the capping layer growth process. The crystallite surface may be modified by repeated exposure to an excess of a competing coordinating group. For example, a dispersion of the capped quantum dot may be  
10 treated a coordinating organic compound, such as pyridine, to produce crystallites which dispersed readily in pyridine, methanol, and aromatics but no longer dispersed in aliphatics. Such a surface exchange process may be carried out using a variety of compounds which are capable of coordinating or bonding to the outer surface of the capped quantum dot, such as by way of example, phosphines, thiols, amines and  
15 phosphates. In other embodiments, the capped quantum dots may be exposed to short chained polymers which exhibit an affinity for the capped surface on one and which terminate in a moiety having an affinity for the suspension or dispersion medium. Such affinity improves the stability of the suspension and discourages flocculation of the capped quantum dots.

20 The synthesis described above produces overcoated quantum dots with a range of core and shell sizes. Significantly, the method of the invention allows both the size distribution of the nanocrystallites and the thickness of the overcoating to be independently controlled. Figure 1 shows the absorption spectra of CdSe dots with a particle size distribution of (a) 23 Å, (b) 42 Å, (c) 48 Å and (d) 55 Å in diameter  
25 before (dashed lines) and after (solid lines) overcoating with 1-2 monolayers of ZnS. By "monolayer" as that term is used herein, it is meant a shell of ZnS which measures 3.1 Å (the distance between consecutive planes along the [002] axis in the bulk wurtzite ZnS) along the major axis of the prolate shaped dots. The absorption spectra represents the wavelength and intensity of absorption of light which is absorbed by  
30 the quantum dot. Figure 1 indicates a small shift in the absorption spectra to the red (lower energies) after overcoating due to the partial leakage of the exciton into the ZnS matrix. This red shift is more pronounced in smaller dots where the leakage of

the exciton into the ZnS shell has a more dramatic effect on the confinement energies of the charge carriers.

Figure 2 shows the room temperature photoluminescence spectra (PL) of the samples shown in Figure 1 before (dashed lines) and after (solid lines) overcoating with ZnS. The PL quantum yield increases from 5-15% for bare dots to values ranging from 30% to 50% for dots passivated with ZnS. The PL spectra are much more intense due to their higher quantum yield of (a) 40%, (b) 50%, (c) 35% and (d) 30%, respectively. The quantum yield reaches a maximum value with the addition of approximately 1.3 monolayers of ZnS. A decrease in quantum yields at higher ZnS coverages may be due to the formation of defects in the ZnS shell.

Figure 3 is a color photograph which demonstrates the wide spectral range of luminescence from the (CdSe)ZnS composite quantum dots of the present invention. The photograph shows six different samples of ZnS overcoated CdSe dots dispersed in dilute hexane solutions and placed in identical quartz cuvettes. The samples were irradiated with 356 nm ultraviolet light from a uv lamp in order to observe luminescence from all solutions at once. As the size of the CdSe core increased, the color of the luminescence shows a continuous progression from the blue through the green, yellow, orange to red. Their PL peaks occur at (going from right to left in Figure 3) (a) 470 nm, (b) 480 nm, (c) 520 nm, (d) 560 nm, (e) 594 nm and (f) 620 nm. In contrast, in the smallest sizes of bare TOPO-capped dots, the color of the PL is normally dominated by broad deep trap emissions and appears as faint white light.

In order to demonstrate the effect of ZnS passivation on the optical and structural properties of CdSe dots, a large quantity of  $\sim 40 \text{ \AA}$  ( $\pm 10\%$ ) diameter CdSe dots were overcoated with varying amounts of Zn and S precursors under identical temperatures and variable times. The result was a series of samples with similar CdSe cores, but with varying ZnS shell thicknesses. Figure 4 shows the progression of the absorption spectrum for these samples with ZnS coverages of approximately 0 (bare TOPO capped CdSe), 0.65, 1.3, 2.6 and 5.3 monolayers. The right hand side of the figure shows the long wavelength region of the absorption spectra showing the lowest energy optical transitions. The spectra demonstrate an increased red-shift with the thicker ZnS overcoating as well as a broadening of the first peak in the spectra due to increased polydispersity of shell thicknesses. The left hand side of the spectra show

the ultra-violet region of the spectra indicating an increased absorption at higher energies with increasing ZnS thickness due to direct absorption into the higher ZnS band gap ZnS shell.

5 The evolution of the PL for the same  $\sim 40$  Å diameter CdSe dots with ZnS coverage is displayed in Figure 5. As the coverage of ZnS on the CdSe surface increases one observes a dramatic increase in the fluorescence quantum yield followed by a steady decline after  $\sim 1.3$  monolayers of ZnS. The spectra are red shifted (slightly more than the shift in the absorption spectra) and show an increased broadening at higher coverages. The inset to Figure 5 charts the evolution of the  
10 quantum yield for these dots as a function of the ZnS shell thickness. For this particular sample, the quantum yield started at 15% for the bare TOPO capped CdSe dots and increased with the addition of ZnS approaching a maximum value of 50% at approximately  $\sim 1.3$  monolayer coverage. At higher coverages, the quantum yield began to decrease steadily until it reached a value of about 30% at about 5  
15 monolayers coverage.

Although the invention has been described with reference to the preparation and performance of CdSe(ZnS), it will be readily apparent that the method of preparation may be used to obtain monodisperse overcoated quantum dots with  
various combinations of nanocrystallite core and overcoating. The method of the  
20 invention permits the preparation of a variety of capped nanocrystals having a very narrow particle size distribution and exhibiting improvements in color purity and intensity of their photoluminescent emissions. It is contemplated that a variety of cadmium chalcogenides, for example, CdX, where X = S, Se, Te may be prepared and overcoated according to the method of the invention. It is further contemplated that  
25 the overcoating may be varied and may include, by way of example only, ZnS, ZnSe, CdS and mixtures thereof.

The invention is described with reference to the following examples, which are presented for the purpose of illustration and which are not intended to be limiting of the invention, the scope of which is set forth in the claims which follow this  
30 specification.

Example 1. Preparation of CdSe. Trioctylphosphine oxide (TOPO, 90% pure) and trioctylphosphine (TOP, 95% pure) were obtained from Strem and Fluka,

respectively. Dimethyl cadmium ( $\text{CdMe}_2$ ) and diethyl zinc ( $\text{ZnEt}_2$ ) were purchased from Alfa and Fluka, respectively, and both materials were filtered separately through a  $0.2\mu\text{m}$  filter in an inert atmosphere box. Trioctylphosphine selenide was prepared by dissolving 0.1 mols of Se shot in 100ml of TOP thus producing a 1M solution of TOPSe. Hexamethyl(disilathiane) ( $\text{TMS}_2\text{S}$ ) was used as purchased from Aldrich. HPLC grade

n-hexane, methanol, pyridine and n-butanol were purchased from EM Sciences.

The typical preparation of TOP/TOPO capped CdSe nanocrystallites follows. TOPO (30g) was placed in a flask and dried under vacuum ( $\sim 1$  Torr) at  $180^\circ\text{C}$  for 1 hour. The flask was then filled with nitrogen and heated to  $350^\circ\text{C}$ . In an inert atmosphere drybox the following injection solution was prepared:  $\text{CdMe}_2$  (200 microliters, 2.78 mmol), 1 M TOPSe solution (4.0 mL, 4.0 mmol), and TOP (16 mL). The injection solution was thoroughly mixed, loaded into a syringe, and removed from the drybox.

The heat was removed from the reaction flask and the reagent mixture was delivered into the vigorously stirring TOPO with a single continuous injection. This produces a deep yellow/orange solution with a sharp absorption feature at 470-500 nm and a sudden temperature decrease to  $\sim 240^\circ\text{C}$ . Heating was restored to the reaction flask and the temperature was gradually raised to  $260\text{-}280^\circ\text{C}$ .

Aliquots of the reaction solution were removed at regular intervals (5-10 min) and absorption spectra taken to monitor the growth of the crystallites. The best samples were prepared over a period of a few hours steady growth by modulating the growth temperature in response to changes in the size distribution, as estimated from the sharpness of the features in the absorption spectra. The temperature was lowered 5-10  $^\circ\text{C}$  in response to an increase in the size distribution. Alternatively, the reaction can also be stopped at this point. When growth appears to stop, the temperature is raised 5-10  $^\circ\text{C}$ . When the desired absorption characteristics were observed, the reaction flask was allowed to cool to  $\sim 60^\circ\text{C}$  and 20 mL of butanol were added to prevent solidification of the TOPO. Addition of a large excess of methanol causes the particles to flocculate. The flocculate was separated from the supernatant liquid by centrifugation; the resulting powder can be dispersed in a variety of organic solvents

(alkanes, ethers, chloroform, tetrahydrofuran, toluene, etc.) to produce an optically clear solution.

Size-selective Precipitation. Nanocrystallites were dispersed in a solution of ~10% butanol in hexane. Methanol was then added dropwise to this stirring solution until opalescence persisted. Separation of supernatant and flocculate by centrifugation produced a precipitate enriched with the largest crystallites in the sample. This procedure was repeated until no further sharpening of the optical absorption spectrum was noted. Size-selective precipitation can be carried out in a variety of solvent/nonsolvent pairs, including pyridine/hexane and chloroform/methanol.

Surface Exchange. Crystallite surface derivatization can be modified by repeated exposure to an excess of a competing capping group. Heating to ~60°C a mixture of ~50 mg of TOPO/TOP capped crystallites and 5-10 mL of pyridine gradually dispersed the crystallites in the solvent. Treatment of the dispersion with excess hexane resulted in the flocculation of the crystallites which are then isolated by centrifugation. The process of dispersion in pyridine and flocculation with hexane was repeated a number of times to produce crystallites which dispersed readily in pyridine, methanol, and aromatics but no longer dispersed in aliphatics.

Example 2. Preparation of CdSe. A second route to the production of CdSe core replaces the phosphine chalcogenide precursors in Example 1 with (TMS)<sub>2</sub>Se. The smallest (~12Å) CdSe species are produced under milder conditions with injection and growth carried out at ~100°C. The product was further treated as described in Example 1.

Example 3. Preparation of (CdSe)ZnS. Nearly monodisperse CdSe quantum dots ranging from 23Å to 55Å in diameter were synthesized and purified via size-selective precipitation as described in Example 1.

A flask containing 5g of TOPO was heated to 190°C under vacuum for several hours then cooled to 60°C after which 0.5 mL trioctylphosphine (TOP) was added. Roughly 0.1-0.4 μmols of CdSe dots dispersed in hexane were transferred into the reaction vessel via syringe and the solvent was pumped off.

Diethyl zinc (ZnEt<sub>2</sub>) and hexamethyldisilathiane ((TMS)<sub>2</sub>S) were used as the Zn and S precursors, respectively. The amounts of Zn and S precursors needed to



grow a ZnS shell of desired thickness for each CdSe sample were determined as follows: First, the average radius of the CdSe dots was estimated from TEM or SAXS measurements. Next, the ratio of ZnS to CdSe necessary to form a shell of desired thickness was calculated based on the ratio of the shell volume to that of the core assuming a spherical core and shell and taking into account the bulk lattice parameters of CdSe and ZnS. For larger particles the ratio of Zn to Cd necessary to achieve the same thickness shell is less than for the smaller dots. The actual amount of ZnS that grows onto the CdSe cores was generally less than the amount added due to incomplete reaction of the precursors and to loss of some material on the walls of the flask during the addition.

Equimolar amounts of the precursors were dissolved in 2-4 mL TOP inside an inert atmosphere glove box. The precursor solution was loaded into a syringe and transferred to an addition funnel attached to the reaction flask. The reaction flask containing CdSe dots dispersed in TOPO and TOP was heated under an atmosphere of N<sub>2</sub>. The temperature at which the precursors were added ranged from 140°C for 23 Å diameter dots to 220°C for 55 Å diameter dots. When the desired temperature was reached the Zn and S precursors were added dropwise to the vigorously stirring reaction mixture over a period of 5-10 minutes.

After the addition was complete the mixture was cooled to 90°C and left stirring for several hours. Butanol (5mL) was added to the mixture to prevent the TOPO from solidifying upon cooling to room temperature. The overcoated particles were stored in their growth solution to ensure that the surface of the dots remained passivated with TOPO. They were later recovered in powder form by precipitating with methanol and redispersing into a variety of solvents including hexane, chloroform, toluene, THF and pyridine.

In some cases, the as-grown CdSe crystallites were judged to be sufficiently monodisperse that no size-selective precipitation was performed. Once these CdSe particles had grown to the desired size, the temperature of the reaction flask was lowered and the Zn and S precursors were added dropwise to form the overcapping.

Optical Characterization. UV-Visible absorption spectra were acquired on an HP 8452 diode array spectrophotometer. Dilute solutions of dots in hexane were placed in 1 cm quartz cuvettes and their absorption and corresponding fluorescence

were measured. The photoluminescence spectra were taken on a SPEX Fluorolog-2 spectrometer in front face collection mode. The room temperature quantum yields were determined by comparing the integrated emission of the dots in solution to the emission of a solution of rhodamine 590 or rhodamine 640 of identical optical density

5 at the excitation wavelength.

What is claimed is:

- 1           1.     A coated nanocrystal capable of light emission, comprising:  
2                 a core selected from the group consisting of CdX, where x = S, Se, Te, and  
3                 mixtures thereof, said core being a member of a substantially monodisperse particle  
4                 population; and  
5                 an overcoating of ZnY, where Y = S, Se, uniformly deposited thereon, said  
6                 coated core characterized in that when irradiated the particles emit light in a narrow  
7                 spectral range of no greater than about 60 nm at full width half max (FWHM).  
8  
9           2.     A coated nanocrystal capable of light emission, comprising:  
10                a core selected from the group consisting of CdX, where x = S, Se, Te, and  
11                mixtures thereof, said core being a member of a substantially monodisperse particle  
12                population; and  
13                an overcoating of ZnY, where Y = S, Se, uniformly deposited thereon, said  
14                coated core characterized in that the nanocrystal exhibits less than a 10% rms  
15                deviation in diameter of the core.  
16  
17           3.     The coated nanocrystal of claim 1, wherein the spectral range is not  
18                greater than about 40 nm at full width half max (FWHM).  
19  
20           4.     The coated nanocrystal of claim 1, wherein the spectral range is not  
21                greater than about 30 nm at full width half max (FWHM).  
22  
23           5.     The coated nanocrystal of claim 1, wherein the coated nanocrystal  
24                exhibits photoluminescence having quantum yields of greater than 30%.  
25  
26           6.     The coated nanocrystal of claim 1, wherein the coated nanocrystal  
27                exhibits photoluminescence having quantum yields in the range of about 30 to 50%.  
28  
29           7.     The coated nanocrystal of claim 2, wherein the coated nanocrystal  
30                exhibits less than a 5% rms deviation in size of the core.  
31

1           8.     The coated nanocrystal of claim 1 or 2, wherein the overcoating  
2 comprises one to two monolayers of ZnY.

3  
4           9.     The coated nanocrystal of claim 1, wherein the narrow spectral range  
5 is selected from the spectrum in the range of about 470 nm to about 620 nm.

6  
7           10.    The coated nanocrystal of claim 2, wherein the particle size of the core  
8 is selected from the range of about 20Å to about 125 Å.

9  
10          11.    The coated nanocrystal of claim 1 or 2, wherein the nanocrystal  
11 further comprises an organic layer on the nanocrystal outer surface.

12  
13          12.    The coated nanocrystal of claim 11, wherein the organic layer is  
14 comprised of moieties selected to provide compatibility with a suspension medium.

15  
16          13.    The coated nanocrystal of claim 11, wherein the organic layer is  
17 comprised of moieties selected to exhibit affinity for the outer surface of the  
18 nanocrystal.

19  
20          14.    The coated nanocrystal of claim 13, wherein the organic layer  
21 comprises a short-chain polymer terminating in a moiety having affinity for a  
22 suspending medium.

23  
24          15.    A method of preparing a coated nanocrystal capable of light emission,  
25 comprising:

26           introducing a substantially monodisperse first semiconductor core population  
27 and a precursor capable of thermal conversion into a second semiconductor material  
28 into a coordinating solvent,

29           wherein the coordinating solvent is maintained at a temperature sufficient to  
30 convert the precursor into the second semiconductor material yet insufficient to  
31 substantially alter the monodispersity of the first semiconducting core,

1            wherein the second semiconductor material has a band gap greater than the  
2 first semiconducting nanocrystal, and

3            whereby an overcoating of the second semiconductor material is formed on  
4 the first semiconducting nanocrystal,

5  
6            16.    The method of claim 15, further comprising:  
7            monitoring the monodispersity of the nanocrystal during conversion of the  
8 precursor and overcoating of the first semiconductor nanocrystal.

9  
10           17.    The method of claim 15, wherein the is was lowered in response to a  
11 spreading of the size distribution as estimated from the absorption spectra.

12  
13           18.    The method of claim 15, wherein the temperature is increased in  
14 response to when monitoring indicates growth appears to stop.

15  
16           19.    The method of claim 15, wherein the first semiconductor crystal is  
17 selected from the group consisting of CdX, where X = S, Se and Te.

18  
19           20.    The method of claim 15, wherein the second semiconductor material is  
20 selected from the group consisting of ZnS, ZnSe, CdS and CdSe and mixtures thereof.

21  
22           21.    The method of claim 15, wherein the particle size of the core is in the  
23 range of about 20Å to about 125 Å.

24  
25           22.    The method of claim 15, wherein the nanocrystal further comprises an  
26 organic layer on the nanocrystal outer surface.

27  
28           23.    The method of claim 22, wherein the organic layer is obtained by  
29 exposing the nanocrystal to an organic compound having affinity for the nanocrystal  
30 surface, whereby the organic compound displaces the coordinating solvent.




Figure 1





Figure 2



Felice Frankel

A B C D E F

Figure 3






Figure 4




Figure 5

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 98/23984

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 H01L33/00

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 H01L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	<p>DABBOUSI B. O. ET AL: "(CDSE)ZNS CORE-SHELL QUANTUM DOTS: SYNTHESIS AND CHARACTERIZATIONS OF A SIZE SERIES OF HIGHLY LUMINESCENT NANOCRYSTALLITES" JOURNAL OF PHYSICAL CHEMISTRY B, vol. 101, no. 46, 13 November 1997, pages 9463-9475, XP002095418 see page 9463 - page 9467; figures 1-5</p> <p style="text-align: center;">--- -/--</p>	1-23



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

### \* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

3 March 1999

Date of mailing of the international search report

06/04/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Berthold, K

# INTERNATIONAL SEARCH REPORT

Int. Application No.  
PC17/US 98/23984

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	MIKULEC F. V. ET AL: "SYNTHESIS AND CHARACTERIZATIONS OF HIGHLY LUMINESCENT(CDSE)ZNS QUANTUM DOTS" ADVANCES IN MICROCRYSTALLINE AND NANOCRYSTALLINE SEMICONDUCTORS, SYMPOSIUM 1996, BOSTON, MA, MATER. RES. SOC. 1997, PITTSBURGH, PA, USA, 2 - 6 December 1996, pages 359-364, XP002095419 see page 359, line 1 - page 364, line 16; figures 1-7	1-23
X	KUNO M. ET AL: "THE BAND EDGE LUMINESCENCE OF SURFACE MODIFIED CDSE NANOCRYSTALLITES: PROBING THE LUMINESCENCE STATE" JOURNAL OF CHEMICAL PHYSICS, vol. 106, no. 23, 15 June 1997, pages 9869-9882, XP002095420 see page 9870 - page 9875; figures 2-4,8	1-23
X	KORTAN A. R. ET AL: "NUCLEATION AND GROWTH OF CDSE ON ZNS QUANTUM CRYSTALLITE SEEDS, AND VICE VERSA, IN INVERSE MICELLE MEDIA" JOURNAL OF THE AMERICAN CHEMICAL SOCIETY, vol. 112, 1990, pages 1327-1332, XP000196554 cited in the application see page 1331, left-hand column, line 37 - page 1332, right-hand column, line 35; figure 2B	1,8-10
X	HINES M.A. ET AL: "SYNTHESIS AND CHARACTERIZATION OF STRONGLY LUMINESCING ZNS-CAPPED CDSE NANOCRYSTALS" J. PHYS. CHEM., vol. 100, 1996, pages 468-471, XP002095446 cited in the application see abstract; figure 3	1,5,6, 8-10
A	MURRAY C. B. ET AL: "SYNTHESIS AND CHARACTERIZATION OF NEARLY MONODISPERSE CDE (E = S, SE, TE) SEMICONDUCTOR NANOCRYSTALLITES" JOURNAL OF THE AMERICAN CHEMICAL SOCIETY, vol. 115, 1993, pages 8706-8715, XP000196555 cited in the application see page 8706, left-hand column, line 1 - page 8708, left-hand column, line 25	1-23